

强邦SF-DGL数码型感光树脂柔性版

强邦SF-DGL是最新的高硬度的数码型感光树脂柔性版,为印刷厂提供了更高的印刷品质以及更快的生产效率。SF-DGL版材具有高分辨率,良好的成像能力,且适用于各种类型的基材和应用。同时我们提升了材料的上墨性能,实现平滑的实地印刷以及印刷过程中的清洁。

产品特性

- ◇ 更高的印刷品质,图像更锐利、浮雕更深、高光网点更完美、网点扩大值更小、阶调范围更宽、印刷反差更大并且在适当的制版设备下完美实现平顶网点
- ◇ 高回弹力以及在印刷机械的冲击下优秀的机械性能带来卓越的耐印率
- ◇ 采用数字工作流程,提高了生产力,减少了故障率,数据传输不会降低图像质量
- ◇ 与水性以及醇溶剂油墨有着良好的匹配和完美的上墨性能
- ◇ 无需菲林,制版成本更低,更加环保
- ◇ 适用于标签、软包装、手提袋、折叠纸盒、薄膜等基材的印刷



Strong State SF-DGL Digital Flexo Plates

SF-DGL is the newest hard durometer digital sheet photopolymer, which delivers higher quality print and increased productivity. SF-DGL sheet photopolymer has fine resolution, imaging capability and will work over a broad range of substrates and applications. Ink transfer is enhanced, delivering extremely smooth solids and crisp, clean running process.

Key Features:

- ◇ Superior printing quality with sharper images, more open intermediate depths, finer highlight dots and less dot gain, i.e. larger range of tonal values therefore improved contrast and produce flat top dots when adequate process equipment are used
- ◇ High resilience and good resistance towards mechanical impacts deliver excellent durability
- ◇ Increased productivity and data transfer without loss of quality due to digital workflow
- ◇ Excellent ink transfer using water and alcohol-based inks
- ◇ Cost effective and more environmentally friendly in processing, as no film is required
- ◇ Suitable for labels, tags, flexible packaging, sacks, folding carton, films and so on



技术指标

Technical Specifications

Thickness 厚度 (mm / inch)	Hardness 硬度 (Shore Å)	Total Range 可再现图像 (%)	Screen Ruling 网线数 (LPI)	Minimum Isolated Line 最细阳线 (mm)	Minimum Isolated Dot 最小独立点 (mm)
1.14/0.045	75	1 – 98%	175	0.1	0.15
1.70/0.067	67	1 – 98%	175	0.1	0.15
2.28/0.090	55	2 – 95%	150	0.1	0.15

推荐的制版条件

Recommended Processing Conditions

Thickness 厚度 (mm / inch)	Back exposure 背曝 (seconds)	Main exposure 主曝 (mins)	Wash out 洗版 (mm/mins)	Dry 烘干 (hours)	Post exposure 后处理 (mins)	Detack 去粘 (mins)
1.14/0.045	40-60	10-15	160-180	1.5-2	5	4
1.70/0.067	50-70	10-15	140-180	1.5-2	5	4
2.28/0.090	60-100	10-15	130-170	2-2.5	5	4

注意事项

1. 请联系您的强邦销售代表, 他会协助您建立适当的制版条件。

2. 所有的制版条件都根据客户具体的制版设备、紫外灯的寿命以及洗版溶剂的不同而做相应的调整。

以上参数仅供参考。

1. Contact your Strong State representative for assistance in establishing proper processing conditions.

2. All processing parameters depend on, among others, the processing equipment, lamp age and the type of washout solvent. The above-mentioned values are only to be used as a guide.



争创卓越品质

诚信服务顾客



上海甚龙新材料技术有限公司

地址：上海市嘉定工业区北区北和公路738号

电话：021-33517708/021-33517777

传真：021-33517788

网址：www.shqiangbang.com

Shanghai Shenlong New Materials Technology CO., Ltd.

No. 738Beihe Road,North Area of JiaDing Industry Zone,Shanghai

Tel: 021-33517708/33517777

Fax: 021-33517788

Web: www.shqiangbang.com