

强邦SF-GL传统型感光树脂柔性版

强邦SF-GL是最新的中等硬度的传统型感光树脂柔性版,为印刷厂提供了更高的印刷品质以及更快的生产效率。SF-GL版材具有出色的回弹力,适应于更快的印刷速度。同时,我们提升了材料的上墨性能,实现平滑的实地印刷以及印刷过程中的清洁。

产品特性

- ◇ 任何一款厚度的产品都有优质的图像保真度和优良的图像网点再现
- ◇ 在任何印刷速度下均保持优良、均匀的印刷效果,无杯形网点
- ◇ 高回弹力以及在印刷机械的冲击下优秀的机械性能带来卓越的耐印率
- ◇ 与水性以及醇溶剂油墨有着良好的匹配和完美的上墨性能
- ◇ 适用于标签、软包装、手提袋、折叠纸盒、薄膜等基材的印刷

Strong State SF-GL Analog Flexo Plates

SF-GL is the newest medium durometer analog sheet photopolymer, which delivers higher quality print and increased productivity. SF-GL sheet photopolymer has exceptional resilience, allowing for faster press speeds and reduced bounce. Ink transfer is enhanced, delivering extremely smooth solids and crisp, clean running process.

Key Features:

- ◇ Image fidelity for high-end graphic and halftone reproduction at all gauges
- ◇ No cupping allows for uniform impression at all process speeds
- ◇ High resilience and good resistance towards mechanical impacts deliver excellent durability
- ◇ Excellent ink transfer using water and alcohol-based inks
- ◇ Suitable for labels, tags, flexible packaging, sacks, folding carton, films and so on



技术指标

Technical Specifications

Thickness 厚度 (mm / inch)	Hardness 硬度 (Shore Å)	Total Range 可再现图像 (%)	Screen Ruling 网线数 (LPI)	Minimum Isolated Line 最细阳线 (mm)	Minimum Isolated Dot 最小独立点 (mm)
1.70/0.067	63	2 – 95%	133	0.15	0.25
2.28/0.090	54	2 – 95%	133	0.15	0.25

推荐的制版条件

Recommended Processing Conditions

Thickness 厚度 (mm / inch)	Back exposure 背曝 (seconds)	Main exposure 主曝 (mins)	Wash out 洗版 (mm/mins)	Dry 烘干 (hours)	Post exposure 后处理 (mins)	Detack 去粘 (mins)
1.70/0.067	10-30	6-12	140-180	1.5-2	5	5
2.28/0.090	15-35	6-12	140-180	1.5-2	5	3

注意事项

1. 请联系您的强邦销售代表, 他会协助您建立适当的制版条件。

2. 所有的制版条件都根据客户具体的制版设备、紫外灯的寿命以及洗版溶剂的不同而做相应的调整。

以上参数仅供参考。

1. Contact your Strong State representative for assistance in establishing proper processing conditions.

2. All processing parameters depend on, among others, the processing equipment, lamp age and the type of washout solvent. The above-mentioned values are only to be used as a guide.



争创卓越品质

诚信服务顾客



上海甚龙新材料技术有限公司

地址：上海市嘉定工业区北区北和公路738号

电话：021-33517708/021-33517777

传真：021-33517788

网址：www.shqiangbang.com

Shanghai Shenlong New Materials Technology CO., Ltd.

No. 738Beihe Road,North Area of JiaDing Industry Zone,Shanghai

Tel: 021-33517708/33517777

Fax: 021-33517788

Web: www.shqiangbang.com